

## PATENT ABSTRACTS OF JAPAN

(11)Publication number : 04-296338

(43)Date of publication of application : 20.10.1992

---

(51)Int.Cl.

C08J 9/06  
// C08L 23/00  
C08L 23/26  
C08L 23:04

---

(21)Application number : 03-132358

(71)Applicant : DU PONT MITSUI POLYCHEM CO  
LTD

(22)Date of filing : 25.03.1991

(72)Inventor : ADACHI YUKIO

---

### (54) CROSSLINKED AND FOAMED MATERIAL

#### (57)Abstract:

PURPOSE: To provide a crosslinked and foamed material having excellent antistaticity, formability and uniformity.

CONSTITUTION: The objective crosslinked and foamed material is made of a resin composition composed of 20-75wt.% of an ionomer of an ethylene-unsaturated carboxylic acid copolymer containing potassium as the ion source and having an average neutralization degree of  $\geq 50\%$  and 80-25wt.% of an olefin polymer. The ionomer containing 18-35wt.% of unsaturated carboxylic acid accounts for  $\geq 10\text{wt.}\%$  in the above composition and the expansion ratio of the material is  $< 20\%$ . The crosslinked and foamed material produced by this process is easily formable and has excellent cushioning property, heat-resistance and antistaticity and is useful as a cushioning material for electric and electronic parts, etc.

---

### LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office